



# POWERCOAT

## สีรองพื้นกันสนิม พาวเวอร์โค้ท GREY/RED OXIDE PRIMER

Great Value Red Oxide Primer

“สีรองพื้นกันสนิม พาวเวอร์โค้ทสีเทาและน้ำตาลแดง”คุณภาพเต็มถึงในราคาที่คุณพอใจ เป็นสีรองพื้นกันสนิม (Alkyd System) สามารถทาทับได้ด้วยสีน้ำมัน ใช้ทาหรือชุบเพื่อปกป้องโครงสร้างเหล็กต่างๆจากการผุกร่อนและเป็นสนิม มีส่วนผสมของ Red Oxide ที่ช่วยปกป้องการผุกร่อนและสนิมได้ดี เหมาะสำหรับงานโครงสร้างเหล็ก อุตสาหกรรม งานเรือ และงานเหล็กทั่วไป

“PowerCoat Red Oxide and Grey Primer” is a QuickDry primer for alkyd system, prior to the application of Alkyd Enamel. The corrosive resistant pigments of the oxide primer make it an ideal choice for use on farm equipments, railings, window frames, fences, steel structure, pipes, field machinery and storage tanks to act as protection from corrosion.



### AVAILABLE COLOURS:



รองพื้นกันสนิมแดง  
Red Oxide Primer



รองพื้นกันสนิมเทา  
Grey Oxide Primer



ขนาดบรรจุ 1 ถึง  
Packing size 1 Drum



เหมาะสำหรับ พารองพื้นกันสนิมเหล็ก  
Prupose Primer/Shop Primer for Steel



แห้งเร็วมาก ทาทับได้ด้วย สีน้ำมัน  
Recoating With Alkyd Paint



ระยะเวลาแห้งผิว 30-60 นาที  
Surface Drying time 30-60 Minutes

PowerCoat Red/Grey Oxide Primer can be used as a primer on metal surfaces where an alkyd system is required. Surface preparation and Application All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

- **Brush** - Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.
- **Roller**: May be used. However when using roller application care must be taken to apply sufficient material in order to achieve the specified dry film thickness.

Condition during application The temperature of the substrate should be minimum 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure correct drying.

#### Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Pack size 1 Drum

Health and safety Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Distribute By Kasemponggrat Group 923/102 T.M,Y Ekachai Road Mehachai, Muang, Samut Sakhon, Thailand 74000 Email: Sales@kasemponggrat.com



PREMIUM COATING